



**4060  
Grit-o'Cob®**

DERIVED FROM THE WOODY PORTION OF THE CORN COB

**PARTICLE SIZE DISTRIBUTION - SCREEN ANALYSIS**

U.S. Standard Mesh			<b>Delphi</b>	<b>Mt. Pulaski</b>	Minimum	Maximum
Pass	Retained		Typical %	Typical %	%	%
-	40		0.9	0.9	0	1
40	50		60	61		
50	60		25	23		
60	100		7	13		
100	-100		0.9	0.9	0	1

**SUMMARY OF PHYSICAL PROPERTIES**

Moisture, maximum %		10	Resistance to attrition, %	>98.6
<b>Delphi</b>	Bulk density, lb/ft <sup>3</sup>	19 - 25		
<b>Mt. Pulaski</b>	Bulk density, lb/ft <sup>3</sup>	19 - 25		

This information was derived from analytical and experimental data generated by The Andersons and supplemented by data obtained from manufacturers using various corn cob products in a variety of applications. For properties not listed and specific to your use, contact The Andersons Processing Division.

*Revised April 2013D/MP*

**Grit-o'Cob** is a registered trademark of The Andersons.